

Aluminized Textured Fiberglass Plain

Style Number	1016
Description	FGT745Plain
Coating Face	Gentex® Dual Mirror® Aluminized Fabric

Characteristics

	Test Method	English	Metric
Areal Weight	ASTM D3776	22.0 oz / sq yd	745.0 gms / sq m
Thickness	ASTM D1777	0.025 in	0.64 mm
Breaking Strength	ASTM D5034		
Warp		400.0 lbs	1780.0 N
Fill		300.0 lbs	1335.0 N
Tear Strength	ASTM D1424		
Elmendorf Tear			
Warp		NA	NA
Fill		NA	NA
Flame Resistance	ASTM D6413		
After Flame		1.0 sec	1.0 sec
Char Length		0.50 in	1.3 cm
Radiant Reflectivity	MIL-C-24929A	15.0 sec	15.0 sec

Style Number: 1016

Comprehensive Fabric Line

Field proven for over 50 years, Gentex delivers the most durable aluminized fabrics in the industry. Each roll of Gentex Dual Mirror Aluminized Fabric is thoroughly tested and provides uncompromising function, appearance, and superior performance even in the most demanding applications. With over twenty aluminized fabrics to choose from and an expert team to guide you in your selection, you can be assured you'll get the right fabric for your specific needs. To view and learn more about our full line of fabrics visit, www.gentexcorp.com/aluminizedfabric.

GENTEX®

**DUAL
MIRROR®**