

Aluminized PFR Rayon			
Style Number	1017		
Description	PFR645Herringbone		
Coating Face	Gentex® Dual Mirror® Aluminized Fabric		
Characteristics			
	Test Method	English	Metric
Areal Weight	ASTM D3776	19.0 oz / sq yd	645.0 gms / sq m
Thickness	ASTM D1777	0.035 in	0.89 mm
Breaking Strength	ASTM D5034		
Warp		350.0 lbs	1557.0 N
Fill		180.0 lbs	801.0 N
Tear Strength	ASTM D1424		
Elmendorf Tear			
Warp		35.0 lbs	156.0 N
Fill		35.0 lbs	156.0 N
Flame Resistance	ASTM D6413		
After Flame		2.0 sec	2.0 sec
Char Length		3.0 in	7.6 cm
Radiant Reflectivity	MIL-C-24929A	25.0 sec	25.0 sec

Style Number: 1017

Comprehensive Fabric Line

Field proven for over 50 years, Gentex delivers the most durable aluminized fabrics in the industry. Each roll of Gentex Dual Mirror Aluminized Fabric is thoroughly tested and provides uncompromising function, appearance, and superior performance even in the most demanding applications. With over twenty aluminized fabrics to choose from and an expert team to guide you in your selection, you can be assured you'll get the right fabric for your specific needs. To view and learn more about our full line of fabrics visit, www.gentexcorp.com/aluminizedfabric.

GENTEX®

DUAL
MIRROR®