

Preox® Chloroprene Coated	
Style Number	1150-1
Description	Preox Herringbone
Coating Face	Chloroprene Coated

Characteristics

	Test Method	English	Metric
Areal Weight	ASTM D3776	16.0 oz / sq yd	540 gms / sq m
Thickness	ASTM D1777	0.020 in	0.51 mm
Breaking Strength			
Warp		200.0 lbs	890.0 N
Fill		150.0 lbs	667.0 N
Tear Strength			
Elmendorf Tear	ASTM D1424		
Wales		15.0 lbs	67.0 N
Courses		15.0 lbs	67.0 N
Flame Resistance	ASTM D6413		
After Flame		1.0 sec	1.0 sec
Char Length		0.5 in	1.27 cm
Radiant Reflectivity			

Style Number: 1150-1

Comprehensive Fabric Line

Field proven for over 50 years, Gentex® delivers the most durable aluminized fabrics in the industry. Each roll of Gentex Dual Mirror® Aluminized Fabric is thoroughly tested and provides uncompromising function, appearance, and superior performance even in the most demanding applications. With over twenty aluminized fabrics to choose from and an expert team to guide you in your selection, you can be assured you'll get the right fabric for your specific needs. To view and learn more about our full line of fabrics visit, www.gentexcorp.com/aluminizedfabric.

GENTEX®

**DUAL
MIRROR®**