

Para Aramid / Woven Twill			
Style Number	1350		
Description	Scoured Para Aramid Twill		
Coating Face	Scoured / No Coating		
Characteristics			
	Test Method	English	Metric
Areal Weight	ASTM D3776	8.0 oz / sq yd	290 gms / sq m
Thickness	ASTM D1777	0.021 in	0.51 mm
Tear Strength	ASTM D5034		
Trapezoidal Tear			
Wales		350.0 lbs	1556.9 N
Courses		300.0 lbs	1334.5 N
Tear Strength	ASTM D1424		
Elmendorf Tear			
Wales		26.0 lbs	115.7 N
Courses		35.0 lbs	155.7 N
Flame Resistance	ASTM D6413		
After flame		2.0 sec	2.0 sec
Char length		1.0 in	3.0 cm
Radiant Reflectivity			

Style Number: 1350

Comprehensive Fabric Line

Field proven for over 50 years, Gentex® delivers the most durable aluminized fabrics in the industry. Each roll of Gentex Dual Mirror® Aluminized Fabric is thoroughly tested and provides uncompromising function, appearance, and superior performance even in the most demanding applications. With over twenty aluminized fabrics to choose from and an expert team to guide you in your selection, you can be assured you'll get the right fabric for your specific needs. To view and learn more about our full line of fabrics visit, www.gentexcorp.com/fabric.

GENTEX®

**DUAL
MIRROR®**